

Characteristics

40-515 can be applied directly to steel, galvanized steel, aluminum and certain plastics. Has high filling power and dries quickly. Good stability on vertical surfaces. Easily sanded. Can be painted over with water-based paints.

Physical Characteristics



12 month



2004/42/II B(e)(840) < 840

Application



cleaning



shake well for
2 min



10 cm - 15 cm



1 - 3
max. 80µm



clean valve

Processing tips



Do not apply on substrates coated with alkyd based laquers as surface defects in form of frizziness may be observed.

Due to the multitude of different types of plastic in the market the compatibility with the substrate should be tested in advance for each individual case.

Not suitable for substrates made from polystyrene.

Do not use on thermoplastic paintwork.

Do not apply 2K UP products.

Drying



3 - 5 min

dust dry: 5 min
recoatable: 15 min
Ready for sanding: 45 min

Storage



Store the product in a ventilated place. Keep away from direct exposure to sunlight. Keep between +15°C and 25°C.

Safety



For more informations check the safety data sheet.



This data sheet is for information purpose only. To our knowledge the data provided complies with the latest standard and is based on years of experience in the manufacturing of our products. Copyright: Q-Company Int. GmbH, all rights reserved.